

## DONGRAY® PE WAX

## 300A

CAS NO: 9002-88-4

U.S.FDA 21 CFR 177.1520

### Typical Properties

Characteristics	Data	Unit	Detection Methods
Appearance	White powder		
Viscosity (@140°C)	1100±100	CPS	Brookfield Visco-meter
Softening point	110±1	°C	ASTM E 28
Density (@23°C)	0.92-0.94	g/cm <sup>3</sup>	ASTM D 1505
Hardness (@25°C)	≅3	d-mm	ASTM D 5
Acid Value	0	mg KOH/g	ASTM D 1386

### Application

- Color concentrate (Dispersion Agents)
- Plastics & Polymers
- Adhesives (Hot-melt etc.)
- Inks & Paints
- Coatings
- Cable Filling Compounds
- Lubricants & Mold release agents

### OFFICES

#### CHINA

FENGSHUN DONGLI FINE CHEMICAL INDUSTRY CO.,LTD.  
FENGSHUN ECONOMIC DEVELOPMENT AREA PROJECT 2,  
MEIZHOU CITY, GUANGDONG.

TEL: 086-753-6683688 FAX: 0753-6683669

#### THAILAND

KE LAI LI CHEMICAL (THAILAND) CO.,LTD.  
521/2 MOO 3 TAMBOL PRAKASA MUANG DISTRICT  
SAMUTPRAKARN 10280, THAILAND.

TEL: 662-701-5797-8 FAX: 662-701-5887

### Packing

packed with three-layer kraft paper 25KG per bag.

Remark: the description given in the table, the information and data we confirm that accurate and reliable, but does not guarantee or assume any responsibility, direct or indirect, Since many factors will affect processing and application of our products,so can't replace the user itself to product testing, actual data is subject to the COA and MSDS testing of our goods factory.