

Technical Data Sheet

DONGRAY® OPE WAX 600A

CAS NO: 9002-88-4

符合美国FDA 21 CFR 177.1520

Typical Properties

Characteristics	Data	Unit	Detection Methods
Appearance	Yellowish powder		
Softening point	103 ± 1	$^{\circ}\! \mathbb{C}$	ASTM E 28
Density(@23°C)	0.93	g/cm ³	ASTM D 1505
Hardness (@25℃)	≦ 5	d-mm	ASTM D 5
Acid Value	5±1	mg KOH/g	ASTM D 1386

Application

- Color concentrate (Dispersion Agents)
- Plastics & Polymers
- Adhesives (Hot-melt etc.)
- Inks & Paints
- Coatings
- Cable Filling Compounds
- Lubricants & Mold release agents

OFFICES

CHINA

FENGSHUN DONGLI FINE CHEMICAL INDUSTRY CO., LTD. FENGSHUN ECONOMIC DEVELOPMENT AREA PROJECT 2, MEIZHOU CITY, GUANGDONG.

TEL: 086-753-6683688 FAX: 0753-6683669

THAILAND

KE LAI LI CHEMICAL (THAILAND) CO., LTD. 521/2 MOO 3 TAMBOL PRAKASA MUANG DISTRICT SAMUTPRAKARN 10280, THAILAND.

TEL: 662-701-5797-8 FAX: 662-701-5887

Packing

packed with three-layer kraft paper 25KG per bag.

Remark: the description given in the table, the information and data we confirm that accurate and reliable, but does not guarantee or assume any responsibility, direct or indirect, Since many factors will affect processing and application of our products, so can't replace the user itself to product testing, actual data is subject to the COA and MSDS testing of our goods factory.



our website at:

www.dongraywax.com